

НАЦИОНАЛЬНЫЙ ИССЛЕДОВАТЕЛЬСКИЙ ТОМСКИЙ ГОСУДАРСТВЕННЫЙ УНИВЕРСИТЕТ
РОССИЙСКИЙ ФОНД ФУНДАМЕНТАЛЬНЫХ ИССЛЕДОВАНИЙ
ИНСТИТУТ ПРОБЛЕМ ХИМИКО-ЭНЕРГЕТИЧЕСКИХ ТЕХНОЛОГИЙ СО РАН
АО «ФЕДЕРАЛЬНЫЙ НАУЧНО-ПРОИЗВОДСТВЕННЫЙ ЦЕНТР «АЛТАЙ»
ИНСТИТУТ ФИЗИКИ ПРОЧНОСТИ И МАТЕРИАЛОВЕДЕНИЯ СО РАН
НАУЧНО-ИССЛЕДОВАТЕЛЬСКИЙ ИНСТИТУТ ФАРМАКОЛОГИИ И РЕГЕНЕРАТИВНОЙ МЕДИЦИНЫ
ИМЕНИ Е.Д. ГОЛЬДБЕРГА
ТП «МОДЕЛИРОВАНИЕ И ТЕХНОЛОГИИ ЭКСПЛУАТАЦИИ ВЫСОКОТЕХНОЛОГИЧНЫХ СИСТЕМ»
ТП «МЕДИЦИНА БУДУЩЕГО»
ЯПОНСКОЕ АГЕНСТВО АЭРОКОСМИЧЕСКИХ ИССЛЕДОВАНИЙ
УНИВЕРСИТЕТ ЭДИНБУРГА
ЛИОНСКИЙ УНИВЕРСИТЕТ I ИМ. КЛОДА БЕРНАРА
КОМПАНИЯ MACH I, INC.

ВЫСОКОЭНЕРГЕТИЧЕСКИЕ И СПЕЦИАЛЬНЫЕ МАТЕРИАЛЫ: ДЕМИЛИТАРИЗАЦИЯ, АНТИТЕРРОРИЗМ И ГРАЖДАНСКОЕ ПРИМЕНЕНИЕ

Сборник тезисов
XIV Международной конференции «HEMs-2018»
3–5 сентября 2018 года
(г. Томск, Россия)

Томск
Издательский Дом Томского государственного университета
2018

3. Хмелев В.Н., Шалунова К.В., Цыганок С.Н., Барсуков Р.В., Сливин А.Н., Шалунов А.В. Ультразвуковая коагуляция аэрозолей. Бийск: АлтГТУ, 2010. 228 с.
4. Stepkina M.Y., Kudryashova O.B., Antonnikova A.A. Sedimentation rates of fine aerosols in acoustic and electric field. *Bulletin of the Tomsk Polytechnic University. Geo Assets Engineering*, 2018, vol. 329, no. 3, pp. 62–68.

MECHANICAL PROPERTIES OF MICROSTRUCTURED MAGNESIUM ALLOY, OBTAINED BY SEVERE PLASTIC DEFORMATION

Moskvichev E.N., Skripnyak V.A.

National Research Tomsk State University, Tomsk

E-mail: em_tsu@mail.ru

In present research, the mechanical properties of a sheet microstructured magnesium alloy of the Mg-Mn-Ce system obtained by the methods of intense plastic deformation were investigated. Modification of the coarse-grained structure of light alloys to an ultrafine-grained state is necessary for improving physico-mechanical properties [1, 2]. The use of widely developed processing techniques, such as equal-channel angular pressing and torsion under pressure, is unacceptable for sheet metal samples because of their shape. As alternative to these methods of processing can be new techniques, in particular, groove pressing with subsequent straightening. (GP) In this method, flat samples, cut from sheet metal, are pressed between two grooved parts of the mold, at the same time, large degrees of plastic deformation are realized in the local regions of the sample due to shear. One pressing cycle consists of the following sequences of actions: grooving; straightening ; sample displacement; repeated grooving; straightening. It is assumed that one cycle promotes uniform sample processing. To determine the degree of deformation during the processing of sheet metal by the GP method, a numerical calculation by the finite element method was carried out. Based on the calculation data, an experiment was performed and microstructured samples of magnesium alloy were obtained. A series of mechanical tests and a study of the microstructure were carried out after obtaining the samples. It was found that plastic deformation to 3.48 leads to the formation in the sample of a microstructure with a lognormal distribution of grain sizes lying in the range 0.5 to 8 μm . It was found that microstructural changes affect significantly to the mechanical behavior of the material at axial tension testing. Yield strength and tensile strength increased significantly. The possibility of inhomogeneous deformation is slightly increased due to an increasing of the limiting strain before fracture.

References

1. Kozulin A.A., Skripnyak V.A., Krasnoyevkin V.A., Skripnyak V.V., Karavatskii A.K. An investigation of physico-mechanical properties of ultrafine-grained magnesium alloys subjected to severe plastic deformation. *Russian Physics Journal*, 2015, 57(9), pp. 1261–1267.
2. Krasnoyevkin V.A., Kozulin A.A., Skripnyak V.A. Detection of structural changes and mechanical properties of light alloys after severe plastic deformation. *Journal of Physics: Conference Proceedings*, V. 1760, 020036.