ТЕЗИСЫ ДОКЛАДОВ

INTERNATIONAL WORKSHOP

**«Multiscale Biomechanics and Tribology
of Inorganic and Organic Systems»**

МЕЖДУНАРОДНАЯ КОНФЕРЕНЦИЯ

**«Перспективные материалы с иерархической структурой
для новых технологий и надежных конструкций»**

**VIII ВСЕРОССИЙСКАЯ НАУЧНО-ПРАКТИЧЕСКАЯ
КОНФЕРЕНЦИЯ С МЕЖДУНАРОДНЫМ УЧАСТИЕМ,
ПОСВЯЩЕННАЯ 50-ЛЕТИЮ ОСНОВАНИЯ
ИНСТИТУТА ХИМИИ НЕФТИ**

«Добыча, подготовка, транспорт нефти и газа»

DOI: 10.17223/9785946218412/384

**DEVELOPMENT OF ELECTRON-BEAM EQUIPMENT AND TECHNOLOGY OF
LAYER WELDING OF THE WIRE IN THE CONDITIONS OF ADDITIVE
TECHNOLOGIES**

Fedorov V.V., Klimenov V.A., Batranin A.V., Pardeep Ranga
National Research Tomsk Polytechnic University, Tomsk, Russian Federation

Currently, more and more often, a wide range of additive technologies (or 3D printing technologies) are used to solve problems of obtaining metal products of complex shape with anisotropic properties. If it is necessary to print thick-walled parts with less accuracy (a few millimeters) and greater productivity, the method of dimensional electron beam surfacing with wire is promising. At its core is a vacuum chamber with an electron-beam gun with a plasma emitter and modular manipulators, providing the possibility of layer-by-layer alloying of powders (EBM) or dimensional deposition with wire. The software provides the possibility of modular replacement and synchronized control of all installation organs, according to the task, using digital G - codes. Printing was carried out at an accelerating voltage of 30 kV and a beam current of 15 to 20 mA (depending on the distance from the substrate), thus, the input power varied from 450 to 600 watts. The focused beam (diameter 150 μm) moved in a circular scan 4 mm in diameter. During the work, samples from wires of titanium alloy Ti-6Al-4V and steel AISI 304 were printed on an electron-beam 3D-printer. The study of the quality of the formed samples on the subject of porosity and structural heterogeneity, and hence the mechanical properties was carried out in the work of non-destructive testing methods using computed tomography and methods of mechanical testing and metallography. It is shown that the regulation of the modes of radiation exposure and modes of wire feeding and beam scanning allows obtaining titanium and steel products with high microstructural uniformity and satisfactory mechanical properties, but the problem of reducing macro porosity requires new approaches to optimize microstructural uniformity and porosity.